



LR6-60DG 280~300M



High Efficiency Mono Technology
with advanced 5BB design to improve
power output

10-year Warranty for Materials and Processing;
30-year Warranty for Extra Linear Power Output



Complete System and Product Certifications

IEC 61215, IEC61730, UL1703
ISO 9001:2008: ISO Quality Management System
ISO 14001: 2004: ISO Environment Management System
TS62941: Guideline for module design qualification and type approval
OHSAS 18001: 2007 Occupational Health and Safety



* Specifications subject to technical changes and tests. LONGi Solar reserves the right of interpretation.

Positive power tolerance (0 ~ +5W) guaranteed

High module conversion efficiency (up to 18.1%)

Better energy yield with excellent low irradiance performance and temperature coefficient

Solid PID resistance ensured by solar cell process optimization and careful module BOM selection

Adaptable to harsh environment: passed rigorous salt mist and ammonia tests

40mm frame design enables easy installation and robust mechanical strength


LONGi Solar

Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong District, Shanghai, 201203
Tel: + 86-21-61047332 Fax: +86-21-61047377 E-mail: module@longi-silicon.com
Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

LR6-60DG 280~300M

Design (mm)



Mechanical Parameters

Cell Orientation: 60 (6×10)
 Junction Box: IP67, three diodes
 Output Cable: 4mm², 300mm in length,
 length can be customized
 Weight: 22.5kg
 Dimension: 1664×996×40mm
 Packaging: 26pcs per pallet

Operating Parameters

Operational Temperature: -40 C ~ +85 C
 Power Output Tolerance: 0 ~ +5 W
 Voc and Isc Tolerance: ±3%
 Maximum System Voltage: DC1500V (IEC)
 Maximum Series Fuse Rating: 20A
 Nominal Operating Cell Temperature: 45±2 C
 Application Class: Class II

Electrical Characteristics

Test uncertainty for Pmax: ±3%

Model Number	LR6-60DG-280M		LR6-60DG-285M		LR6-60DG-290M		LR6-60DG-295M		LR6-60DG-300M	
	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT
Maximum Power (Pmax/W)	280	202.4	285	206.1	290	209.7	295	213.3	300	216.9
Open Circuit Voltage (Voc/V)	38.9	35.8	39.2	36.0	39.4	36.2	39.6	36.5	39.9	36.7
Short Circuit Current (Isc/A)	9.08	7.32	9.18	7.40	9.29	7.49	9.39	7.57	9.50	7.66
Voltage at Maximum Power (Vmp/V)	32.5	29.3	32.7	29.5	32.9	29.7	33.2	30.0	33.4	30.2
Current at Maximum Power (Imp/A)	8.62	6.89	8.71	6.97	8.80	7.04	8.89	7.11	8.98	7.18
Module Efficiency(%)	16.9		17.2		17.5		17.8		18.1	

STC (Standard Testing Conditions): Irradiance 1000W/m², Cell Temperature 25 C, Spectra at AM1.5

NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20 C, Spectra at AM1.5, Wind at 1m/s

Temperature Ratings (STC)


Temperature Coefficient of Isc	+0.059%/C
Temperature Coefficient of Voc	-0.330%/C
Temperature Coefficient of Pmax	-0.410%/C

Mechanical Loading


Front Side Maximum Static Loading	5400Pa
Rear Side Maximum Static Loading	2400Pa
Hailstone Test	25mm Hailstone at the speed of 23m/s

I-V Curve


Current-Voltage Curve (LR6-60DG-290M)



Power-Voltage Curve (LR6-60DG-290M)



Current-Voltage Curve (LR6-60DG-290M)



LONGi Solar

Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong District, Shanghai, 201203
 Tel: + 86-21-61047332 Fax: +86-21-61047377 E-mail: module@longi-silicon.com
 Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.